

PETROGRAPHIC
PROPERTIES



MATERIAL:
Raffinato

Type: Quartzite

Location: Ceará

Source: FACL - Faculdade de Tecnologia Cachoeiro de Itapemirim

PHYSICAL • MECHANICAL CHARACTERISTICS	
Apparent Dry Density	2630.00
Comprehensive Strength (Mpa)	147.06
Water Absorption (%)	0.20
Flexural Resistance (Mpa)	19.81
Apparent Porosity (%)	0.52

Recommended Uses

- Commercial
 - Walls
- Residential
 - Fireplaces
- Countertops
 - Bathrooms

