

PETROGRAPHIC
PROPERTIES



MATERIAL:
Mandrak

Type: Quartzite

Location: Bahia

Source: FACI - FACULDADE CACHOEIRO ITAPEMIRIM

PHYSICAL • MECHANICAL CHARACTERISTICS	
Apparent Dry Density	2680.00
Comprehensive Strength (Mpa)	146.62
Water Absorption (%)	0.25
Flexural Resistance (Mpa)	25.15
Apparent Porosity (%)	0.66

Recommended Uses

- Commercial
 - Walls
- Residential
 - Fireplaces
- Countertops
 - Bathrooms

