

PETROGRAPHIC PROPERTIES



MATERIAL:

Sahara Brown

Type: Quartzite

Location: Bahia

Source: FACI - FACULDADE CACHOEIRO DE ITAPEMIRIM

PHYSICAL • MECHANICAL CHARACTERISTICS	
Apparent Dry Density	2610.00
Comprehensive Strength (Mpa)	146.95
Water Absorption (%)	0.33
Flexural Resistance (Mpa)	20.22
Apparent Porosity (%)	0.86

Recommended Uses

- Commercial
 - Walls
- Residential
 - Fireplaces
- Countertops
 - Bathrooms

