

PETROGRAPHIC
PROPERTIES



MATERIAL:

Cappuccino

Type: Quartzite

Location: Ceará

Source: IPT - Instituto de Pesquisas Tecnológicas

PHYSICAL • MECHANICAL CHARACTERISTICS	
Apparent Dry Density	2651.00
Comprehensive Strength (Mpa)	123.70
Water Absorption (%)	0.16
Flexural Resistance (Mpa)	7.30
Apparent Porosity (%)	0.42

Recommended Uses

- Commercial
 - Walls
- Residential
 - Fireplaces
- Countertops
 - Bathrooms

