

PETROGRAPHIC
PROPERTIES



MATERIAL:

Fusion Dark

Type: Quartzite

Location: Bahia

Source: CEPED - Centro de Pesquisas e Desenvolvimento (BA)

PHYSICAL • MECHANICAL CHARACTERISTICS	
Apparent Dry Density	2731.00
Comprehensive Strength (Mpa)	43.61
Water Absorption (%)	0.19
Flexural Resistance (Mpa)	12.82
Apparent Porosity (%)	0.51

Recommended Uses

- Commercial

■ Walls
- Residential

■ Fireplaces
- Countertops

■ Bathrooms

