

PETROGRAPHIC
PROPERTIES



MATERIAL:
Metalicus

Type: Granite
Location: Bahia
Source:

PHYSICAL • MECHANICAL CHARACTERISTICS	
Apparent Dry Density	2944.00
Compreensive Strength (Mpa)	20.78
Water Absorption (%)	0.37
Flexural Resistance (Mpa)	7.96
Apparent Porosity (%)	1.09

Recommended Uses

- Commercial

■ Walls
- Residential

■ Fireplaces
- Countertops

■ Bathrooms

