

PETROGRAPHIC
PROPERTIES



MATERIAL:
Michelangelo Calacatta

Type: Dolomite
Location: Paraná
Source: IPT - Instituto de Pesquisas Tecnológicas

PHYSICAL • MECHANICAL CHARACTERISTICS	
Apparent Dry Density	2838.00
Comprehensive Strength (Mpa)	196.60
Water Absorption (%)	0.16
Flexural Resistance (Mpa)	10.86
Apparent Porosity (%)	0.45

- Recommended Uses
- Residential

■ Interior Walls

■ Commercial

■ External Cladding

■ Interior Countertops

■ Bathrooms

