

PETROGRAPHIC
PROPERTIES



MATERIAL:

Portinari

Type: Marble

Location: Espírito Santo

Source: FACI - FACULDADE CACHOEIRO DE ITAPEMIRIM

PHYSICAL • MECHANICAL CHARACTERISTICS	
Apparent Dry Density	2830.00
Comprehensive Strength (Mpa)	100.52
Water Absorption (%)	0.22
Flexural Resistance (Mpa)	14.68
Apparent Porosity (%)	0.61

Recommended Uses

- Commercial

■ Residential

■ Interior Floor
- Interior Wall

■ Bathrooms

