

PETROGRAPHIC PROPERTIES



NAME: Matrix
TYPE: Granite
LOCATION:

PHYSICAL-MECHANICAL CHARACTERISTICS

Apparent Dry Density (kg/cm ³):	2,77
Compressive Strength (Mpa):	12,94
Water Absorption (%):	0,26
Flexural Resistance (Mpa):	118,8
Apparent Porosity (%):	0,71

SOURCE: Laboratório de Petrologia e Tecnologia