

PETROGRAPHIC PROPERTIES



MATERIAL:

Raggio D Luna

Type: Quartzite

Location: Bahia

Source: CEPED - Centro de Pesquisas e Desenvolvimento (BA)

PHYSICAL · MECHANICAL CHARACTERISTICS	
Apparent Dry Density	2625.00
Comprehensive Strength (Mpa)	109.81
Water Absorption (%)	0.19
Flexural Resistance (Mpa)	11.44
Apparent Porosity (%)	0.49

Recommended Uses

- Commercial
- Residential
- Countertops
- Walls
- Fireplaces
- Bathrooms

